



Test Certificate for Amorphous Silica.

Origin of Amorphous Silica - *Hydrothermal alteration of Ignimbrite and pumice breccia*
Physical form - *fine white powder*
Source of sample - *composite*
Date of Manufacture - *30th August – 3rd October. (Wks 35-39)*
Production quantity - 293.91 Tonnes
Sample identification - MS 6506

PROPERTY	RESULT	TEST METHOD	TESTING AUTHORITY
Moisture Content	1.96%	AS 3583.2	Microsilica New Zealand Lab
Loss on Ignition	5.60%	AS 3583.3	SpectraChem Analytical Ltd
SO ₃	0.04%	XRF	SpectraChem Analytical Ltd
SiO ₂	86.0%	XRF	SpectraChem Analytical Ltd
Fineness < 2µm	56.0%	Sedigraph	Imerys Tableware NZ Ltd
Total Alkali Content (Na ₂ O equiv.)	0.21%	XRF	SpectraChem Analytical Ltd
Chloride Ion	0.03%	XRF	SpectraChem Analytical Ltd
Relative Strength	111%	ASTM C1240	Boral Construction Materials

Shane Coutts
Manager - Microsilica New Zealand.

P O Box 1143, Whangarei,
New Zealand
Phone : + 64 7 345 4710

Web : www.microsilica.co.nz

150 Te Paea Road, Tikitere. Rotorua
New Zealand
Facsimile : + 64 7 345 7481